



◆ Material Property

Symbol	Unit	Condition	Value
μ_i	-	25 °C, $\leq 10\text{kHz}$, $\leq 1\text{mT}$	2000 \pm 25%
B_s	mT	H=1200(A/m), 25 °C, f=10kHz	490
		H=1200(A/m), 100 °C, f=10kHz	370
H_c	A/m	25 °C, f=10kHz	15
		100 °C, f=10kHz	9
T_c	°C	-	>210
f_c	MHz	25 °C	2
P_L	mW/cm ²	400kHz / 50mT, 25 °C	140
		400kHz / 50mT, 100 °C	110
ρ	$\Omega \cdot \text{m}$	-	7
d	kg/m ³	-	4570


PERMEABILITY (μ_i) vs. FREQUENCY




PERMEABILITY (μ_i) vs. TEMPERATURE




PERMEABILITY (μ_a) vs. FLUX DENSITY(B)




POWER LOSS(P_L) vs. TEMPERATURE at 50mT




**POWER LOSS(P_L)
vs. TEMPERATURE at 200mT**



**POWER LOSS(P_L)
vs. FREQUENCY at 25°C**



**POWER LOSS(P_L)
vs. FREQUENCY at 100°C**



**FLUX DENSITY(B)
vs. TEMPERATURE**

